



# UNITED STATES PATENT AND TRADEMARK OFFICE

UNITED STATES DEPARTMENT OF COMMERCE  
United States Patent and Trademark Office  
Address: COMMISSIONER FOR PATENTS  
P.O. Box 1450  
Alexandria, Virginia 22313-1450  
www.uspto.gov

APPLICATION NO.	FILING DATE	FIRST NAMED INVENTOR	ATTORNEY DOCKET NO.	CONFIRMATION NO.
10/565,836	01/25/2006	Noriki Fukunishi	19078-003US1 F05-053US	7651
26211 7590 09/09/2009 FISH & RICHARDSON P.C. P.O. BOX 1022 MINNEAPOLIS, MN 55440-1022			EXAMINER MUROMOTO JR, ROBERT H	
			ART UNIT 3765	PAPER NUMBER
			NOTIFICATION DATE 09/09/2009	DELIVERY MODE ELECTRONIC

**Please find below and/or attached an Office communication concerning this application or proceeding.**

The time period for reply, if any, is set in the attached communication.

Notice of the Office communication was sent electronically on above-indicated "Notification Date" to the following e-mail address(es):

PATDOCTC@fr.com

**UNITED STATES DEPARTMENT OF COMMERCE****U.S. Patent and Trademark Office**

Address : COMMISSIONER FOR PATENTS  
P.O. Box 1450  
Alexandria, Virginia 22313-1450

APPLICATION NO./ CONTROL NO.	FILING DATE	FIRST NAMED INVENTOR / PATENT IN REEXAMINATION	ATTORNEY DOCKET NO.
10565836 053US	1/25/06	FUKUNISHI ET AL.	19078-003US1 F05-

FISH & RICHARDSON P.C.  
P.O. BOX 1022  
MINNEAPOLIS, MN 55440-1022

**EXAMINER**

BOBBY H. MUROMOTO JR

ART UNIT	PAPER
----------	-------

3765	20090902
------	----------

DATE MAILED:

**Please find below and/or attached an Office communication concerning this application or proceeding.**

**Commissioner for Patents**

The status of amendments section of the Examiner's Answer dated

**(4) Status of Amendments After Final**

The appellant's statement of the status of amendments after final rejection contained in the brief is incorrect.

The claims attached to appeal brief dated 4/22/2009 reflected claims as of 11/17/2008. The current claims should be the claims as entered on 4/14/2009 (shown below).

1. (Currently Amended) A fabric having a thickness of 0.07 mm or less and comprising a rip stop weave wherein the rip widths of the longitude and latitude thereof are each 5 mm or less wherein the tear strength in the warp cut direction and that in the weft cut direction according to the pendulum method are each from 10 to 50 N, the weight per square-meter is 50 g/m<sup>2</sup> or less, the air permeability is 1.5 cm<sup>3</sup>/cm<sup>2</sup>"s or less, and the yarn linear density is 25 dtex or less.

2. (Original) The fabric according to claim 1, wherein the bending rigidity according to KES is 0.025 gfcm<sup>2</sup>/cm or less.

3 - 4. (Canceled)

5. (Previously Presented) The fabric according to claim 1, wherein the cover factor is from 1600 to 2000.

6. (Previously Presented) The fabric according to claim 2, wherein the cover factor is from 1600 to 2000.

7. (Previously Presented) The fabric according to claim 1, wherein the ratio of the warp density to the weft density is from 0.9 to 1.2.

8. (Previously Presented) The fabric according to claim 2, wherein the ratio of the warp density to the weft density is from 0.9 to 1.2.

9.-10. (Canceled)

11. (Previously Presented) The fabric according to claim 1, comprising a polyamide multifilament wherein the fiber fineness is 1.2 dtex or less.
12. (Previously Presented) The fabric according to claim 2, comprising a polyamide multifilament wherein the fiber fineness is 1.2 dtex or less.
13. (Previously Presented) The fabric according to claim 1, comprising a nylon 6 multifilament wherein the fiber fineness is 1.2 dtex or less.
14. (Previously Presented) The fabric according to claim 2, comprising a nylon 6 multifilament wherein the fiber fineness is 1.2 dtex or less.
15. (Currently Amended) The fabric according to claim 1, comprising a rip stop weave wherein the tip .0\_p\_widths of the longitude and latitude thereof are each 1.5 mm or less.
16. (Currently Amended) The fabric according to claim 1, wherein the rip widths of" the longitude and latitude of the rip stop weave are each 1.5 mm or less.
17. (Currently Amended) A fabric having a thickness of 0.07 mm or less and comprising a rip stop weave wherein the rip widths of the longitude and latitude thereof are each 5 mm or less wherein the tear strength in the warp cut direction and that in the weft cut direction according to the pendulum method are each from 10 to 50 N, the weight per square-meter is 50 g/m<sup>2</sup> or less, the air permeability is 1.5 cm<sup>3</sup>/cm<sup>2</sup>"s or less, and the yarn linear density is 25 dtex or less, wherein the fabric is without resin finish and double side calendaring.
18. - 20 (Canceled)
21. (Previously Presented) The fabric according to claim 17, wherein the bending rigidity according to KES is 0.025 gfcm<sup>2</sup>/cm or less.
22. (Previously Presented) The fabric according to claim 17 with single side calendaring.
23. (Previously Presented) The fabric according to claim 21 with single side calendaring.
24. (Previously Presented) The fabric according to claim 1, wherein the glossiness of one surface is 3.0 or less.
25. (Previously Presented) The fabric according to claim 2, wherein the glossiness of one surface is 3.0 or less.

/Bobby Muromoto/  
Primary Examiner Art unit 3765  
9/2/2009